

Our Vertical Integration
Process Ensures Superior
Quality & Value

By manufacturing our own cord and fabric, owning rubber tree plantations and belt molds, and mixing chemicals to create our own compounds we eliminate reliance on external manufacturers for essential materials. This guarantees top quality belts and eliminates inflated pricing.

BECAUSE TESTING PROVES OUR BELTS ARE THE BEST!

In independent testing conducted by the Akron Rubber Development Laboratory, Inc.*, D&D belts outperformed Browning belts in overall break force strength, outperforming them by an average of 34.7% across all four samples tested. Additionally, in the same third-party tests for elongation, D&D belts performed within an average of 1.16%.

This clearly shows our belts not only match but often exceed the quality of those from an industry leader, and are offered at a more competitive price thanks to our vertical integration manufacturing process.

It's a win-win for both our partners and their customers.

* Independent testing results available upon request.

TOP SALES & SUPPORT

- Over 60 sales & customer service reps
- Phones answered by real people
- Online inventory search & order portal
- Quick response times
- Midwest nice

Rock Valley, IA Phoenix, AZ Dallas, TX



98% Orders ship same day 165,000 sqft

Total warehouse space

~\$22m

Inventory in stock

35,000+

Unique SKU's

Testing Results

BX85E

Manufacturer	Maximum Elongation,%	Breaking Strength, lbf
D&D	8.61	3003
Browning	7.51	2816.4

AX50E

Manufacturer	Maximum Elongation, %	Breaking Strength, lbf
D&D	6.85	1814.43
Browning	7.59	1922

B97

Manufacturer	Maximum Elongation, %	Breaking Strength, lbf
D&D	8.90	2980
Browning	8.36	3193.18

3VX670E

Manufacturer	Maximum Elongation, %	Breaking Strength, lbf
D&D	8.03	1747.6
Browning	4.31*	742

^{*} Low elongation is a result of premature breaking before elongation could occur

Our Global Partners Who Trust D&D:

















